

BRASS RODS FOR HOT STAMPING

	Cu	Ni	Sn	Pb	Fe	Al	As	Zn
CuZn40Pb2 CW617N	57.0 - 59.0	0.3 max	0.3 max	1.6 - 2.5	0.3 max	0.05 max	-	diff.
CuZn39Pb2Sn CW613N	57.0 - 59.0	0.3 max	0.2 - 0.5	1.6 - 2.5	0.4 max	0.1 max	-	diff.
CuZn39Pb2 CW612N	59.0 - 60.0	0.3 max	0.3 max	1.6 - 2.5	0.3 max	0.05 max	-	diff.
CuZn38Pb2 CW608N	60.0 - 61.0	0.3 max	0.2 max	1.6 - 2.5	0.2 max	0.05 max	-	diff.
CuZn38Pb1 CW607N	60.0 - 61.0	0.3 max	0.2 max	0.8 - 1.6	0.2 max	0.05 max	-	diff.
CuZn36Pb2As CW602N	61.0 - 63.0	0.3 max	0.1 max	1.7 - 2.8	0.1 max	0.05 max	0.02 - 0.15	diff.
CuZn40Pb1Al CW616N	57.0 - 59.0	0.2 max	0.2 max	1.0 - 2.0	0.2 max	0.05 - 0.30	-	diff.
CuZn39Sn1 CW719R	59.0 - 61.0	0.2 max	0.5 - 1.0	0.2 max	0.1 max	-	-	diff.