

COPPER CATHODE

Composition in %

Sn	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni
99.9802	<0.0001	<0.0001	<0.0001	<0.0001	0.0001	<0.0001	0.0001	<0.0001	<0.0001

P	Pb	S	Sb	Se	Si	Sn	Te	Zn	O
<0.0001	0.0004	0.0180	<0.0001	<0.0001	0.0012	<0.0001	<0.0001	<0.0001	0.1400